

Customer: Contact person: EFBE Date of Order: Fax-No.: LAMINAR ENT. CO. LTD. Simon Chang 2013-01-08 +886 4 25 39 19 73

Landabsatz 25, D-45731 Waltrop tel + 49 (0) 2309 78407-0 fax -10 info@efbe.de www.efbe.de

Testreport Maximum load + Overload test

Bicycle handlebar + stem Test item no. 134152

Test sample data

-	handlebar		stem
Manufacturer	Lagear		Lagear
Model name	HB-MBR 780/35		LB 35 A
Identity no.	No		No
weight (g)	268		194
Suspension		No	
Coating	Yes		Yes
Width / clamping width (mm)	780 / 680		
Clamping torque (Nm)	6		6
Clamping diameter (mm)	34,9		28,6
Length stem (mm)	- ,-		100
Remarks	None		

Test description (LÜF_L)

Max./Overload test handlebar/stem EFBE left (LÜF_L)

The **test arrangement** is corresponding to EN 14766, clause 4.7.6.2. Load input is 50 mm from the <u>left bar</u> <u>end</u> parallel to the handlebar stem. The pneumatically applied test force is detected by the cylinder pressure with a precision pressure gauge. The measurement deviation is ± 3 percent and the duration of force application is 10 s for maximum load and 1 second for overload. The permanent deformation is measured at the load input point in direction of the load.

EFBE-recommendations are:

A Maximum load test		B Overload test	
Load 1:	1 100 N	Load 2:	1 500 N
max. perm. deformation: Fracture behavior:	10 mm no crack / fracture	Fracture behavior:	no brittle fracture

Test result:

A Maximum load test:		B Overload test:	B Overload test:		
Test load 1:	1 100 N	Test load 2:	1 500 N		
Permanent deformation:	3.3 mm	Crack/fracture/deforr	m.: Yes		
Crack or fracture:	No	Brittle fracture:	No		
The Maximum load test was passed.		The Overload test w	The Overload test was passed.		
Remarks: For preceeded tests please see testreport No. P1306487.					
	Otable and				

l est engineer:	I.A. V. Stobberg		
End of testing:	2013-01-17	Waltrop 2013-01-21	

stamp, sign

This test report may not be reproduced but with complete wording. It contains the result of a one-time type testing and no statements about quality of serial production components are made. Readings of dimensions, torques and weights without engagement.